Lubrication

AFB-LF Grease

THK Original Grease

AFB-LF Grease

- Base oil: refined mineral oil
- Consistency enhancer: lithium-based



AFB-LF Grease is a general-purpose grease that provides excellent extreme pressure performance and mechanical stability properties through the use of a refined mineral oil base oil and a lithium-based consistency enhancer.

[Features]

- (1) Extreme pressure resistance
 - The action of the special additives provides higher wear resistance and extreme pressure resistance than other lithium-based greases available on the market.
- (2) Mechanical stability
 - AFB-LF Grease is not easily softened and demonstrates excellent mechanical stability even when used for a long period of time.
- (3) Long service life
 - It provides many times the lubrication life of general lithium soap-based greases. As a result, it offers a lower maintenance workload and greater economy due to the longer intervals between greasing.

[Representative Physical Properties]

| [.top:oon.talito : .tjoida. : opo.tao] | | | |
|---|------------|----------------------|---------------|
| Item | | Representative value | Test method |
| Consistency enhancer | | Lithium-based | |
| Base oil | | Refined mineral oil | |
| Base oil kinematic viscosity: mm²/s (40°C) | | 170 | JIS K 2220 23 |
| Worked penetration (25°C, 60 W) | | 275 | JIS K 2220 7 |
| Mixing stability (100,000 W) | | 345 | JIS K 2220 15 |
| Dropping point: ℃ | | 193 | JIS K 2220 8 |
| Evaporation amount: mass% (99°C, 22 h) | | 0.4 | JIS K 2220 10 |
| Oil separation rate: mass% (100℃, 24 h) | | 0.6 | JIS K 2220 11 |
| Copper plate corrosion (B method, 100℃, 24 h) | | Accepted | JIS K 2220 9 |
| Low-temperature torque: mN·m (-20°C) | Starting | 130 | JIS K 2220 18 |
| | Rotational | 51 | |
| 4-ball testing (welding load): N | | 3089 | ASTM D2596 |
| Service temperature range: °C | | -15 to 100 | |
| Color | | Brownish yellow | |

[Comparison of Grease Service Life Data]

Travel distance until flaking occurs

